

## **How accurate is material data?**

This brief will attempt to give guidance on the accuracy of material data reported in various sources.

There are three main sources for the scatter in reported property values.

- 1) Measurement error & sample preparation.
- 2) Sample composition variation.
- 3) Heat-treatment variation.

The variation due to measurement error and sample preparation can be seen in round-robin studies. These studies typically involve a large amount of material from one batch being divided up and sent to several different laboratories for testing. All laboratories should follow the same testing standard. The magnitude of this error should be the smallest possible. Also note that laboratories which take part in these types of studies are probably the most careful, not all labs will be as careful or as well maintained.

The variation due to composition variation will depend on the specifics of the material being tested. Some metals have wide composition ranges, some pure metals are very sensitive to impurities, some are stable at RT but age or anneal at high temperatures. If the material is not stable over the measurement range, then a repeat measurement will give different results. The glass phase in some ceramics is unstable at high temperatures. Many polymers are sensitive to moisture and to the mold geometry. Glasses and polymers are sensitive to the cooling rate. The thermal, electrical, and magnetic properties of metal at low temperatures are very sensitive to composition and impurities, especially for the purer alloys, and the spread in values will be correspondingly larger than at RT. The size of the test sample can also have an effect due to texture or different cooling rates for the inner and outer material.

Heat treatments are frequently ill-defined. They may say “annealed” or “aged” where the exact time and temperature are not specified, or a range of temperature/times may be given. Annealing conditions can change from manufacturer to manufacture or from year to year but the material just described as “annealed”.

All values given for the spread in the individual properties are approximate and are meant to guide your expectations. I’ve never seen error bars on an FEA simulation.

Property	Typical range on values	Notes	Reference
Thermal expansion data	+/-5% pure materials +/-10% alloys		13
Thermal Conductivity	+/-15% to +/-20%	laser flash	1, 17
Thermal Diffusivity	+/-10% to +/-20%	laser flash	1, 17, 18
Specific heat/Heat capacity	+/-15%	DSC	1, 17
Electrical resistivity/conductivity	+/-15%	estimated from limited data	17
Elastic properties (E, G, v, K)	+/-5% (Ultrasonic) +/-10% (stress-strain curve)	Poisson's ratio is a calculated value, the error will be correspondingly higher	2, 6, 10, 15
Stress-strain curves & Strength (UTS, YS & % elongation)	+/-10% to +/-25% (stress) +/-50% (% elongation)		7, 8, 9, 10, 16
Fatigue (S-N)	+/-20% on stress, 10x on cycles		3, 8, 9
Fatigue (ε-N)	+/-50% on strain, 10x on cycles		4
Stress rupture, Creep strength & Isochronal creep	+/-25% in stress		5, 6, 8, 9
Flexural strength/modulus (polymers)	+/-10%	estimated	
Specific volume	+/-5%	estimated	
Vapor pressure	for low temperature materials: +/-10% near boiling point, for high temperature materials: up to 2x, larger far below the boiling point.	low temperature materials: high temperature materials:	19, 20, 21 22, 23, 24
Viscosity	+/-10% for liquids +/-50% for glasses	estimated from limited data	
Surface tension	+/-10%	estimated from limited data	
Emissivity	+/-30%	very sensitive to the surface condition	14
Magnetic properties	+/-5%	Estimated	
Refractive Index	+/-0.1%		11
Permittivity (dielectric constant)	+/-5%	estimated from limited data	12
Dissipation factor (dielectric loss)	+/-20%	estimated from limited data	12
Seebeck coefficient	+/-6%	From round robin study. Routine measurements are probably higher.	17

## References

1. H. Wang, et. al., "Transport Properties of Bulk Thermoelectrics: An International Round-Robin Study, Part II: Thermal Diffusivity, Specific Heat, and Thermal Conductivity", Journal of Electronic Materials, v42, No. 6, p1073 (2013)
2. A. Wolfenden, M.R. Harmouche, G.V. Blessing, Y.T. Chen, P. Terranova, V. Dayal, V.K. Kinra, J.W. Lemmens, R.R. Phillips, J.S. Smith, P. Manhmoodi, and R.J. Wann, "Dynamic Young's Modulus Measurements in Metallic Materials: Results of an Interlaboratory Testing Program", Journal of Testing and Evaluation, JTEVA, v17, No. 1, p2 (1989)
3. Y. Cui, M. Sauzay, C. Caes, P. Bonnaillie, and B. Arnal, "Modeling and experimental study of long term creep damage in austenitic stainless steels", Procedia Materials Science, v3, p122 (2014)
4. M. Kitagawa, K. Yamaguchi, Y. Fukuda, R. Komine, and H. Hirata, "Analysis of VAMAS Low Cycle Fatigue Round Robin Test in Japan", ISIJ International, v33, No. 8, p817 (1993)
5. J.V. Gluck and J.W. Freeman, "Intermediate Temperature Creep And Rupture Behavior Of Titanium And Titanium-Base Alloys", WADC Technical report 54-112, AD0049022, PB119041 (1954) available online at <http://contrails.iit.edu/items/show/2803>
6. "F.J. Gillig and G.J. Guarnieri, "A Study Of The Tensile And Creep-Rupture Properties Of Fifteen Heats Of C-110M Titanium Alloy Sheet", WADC Technical report 56-164, AD0091903, PB138990 (1956) available online at <http://contrails.iit.edu/reports/3490>
7. A. Greene, H. Sieber, D. Wells and T. Wolfe, "Research Investigation To Determine Mechanical Properties Of Nickel And Cobalt-Base Alloys For Inclusion In Military Handbook-5, Volume I", ML-TDR-64-116, AD0608813 (1964) available online at <http://contrails.iit.edu/reports/8030>
8. "Mechanical Properties Test Data for Structural Materials Quarterly Progress Report for Period Ending July 31, 1974", compiled by M.R. Hill, Report ORNL-4998, Oak Ridge National Laboratory (1974) available online at <https://www.osti.gov/servlets/purl/4282602>
9. "Mechanical Properties Test Data for Structural Materials Quarterly Progress Report for Period Ending October 31, 1976", compiled by M.R. Hill, Report ORNL-5237, Oak Ridge National Laboratory (1976) available online at <https://www.osti.gov/servlets/purl/7325064>
10. J. Carroll, Z. Casias, and J Rodelas, "Round Robin Tensile Testing of 50% cold worked Nitronic 60", SAND-2019-6167 676076 (2019) available online at <https://www.osti.gov/biblio/1762635>
11. Advanced Optics, Schott North America, "TIE-29, Refractive Index and Dispersion", available online at <https://www.schott.com/en-us/products/optical-glass-p1000267/downloads>
12. L.-Y. Chen, P.G. Neudeck, D.J. Spry, G.M. Beheim and G.W. Hunter, "500°C Electronic Packaging and Dielectric Materials for High Temperature Applications", NASA Document ID 20170003040, presented at the 2016 IEEE National Aerospace and Electronics Conference (NAECON) and Ohio Innovation Summit (OIS) available online at <https://ntrs.nasa.gov/citations/20170003040>
13. Y.S. Touloukian, R.K. Kirby, R.E. Taylor, and P.D. Desai, "Thermophysical properties of matter - the TPRC data series. Volume 12. Thermal expansion metallic elements and alloys", ADA129115 available online at <https://ntrl.ntis.gov/NTRL/dashboard/searchResults/titleDetail/ADA129115.xhtml>

14. Y.S. Touloukian and D.P. DeWitt, "Thermophysical properties of matter - the TPRC data series. Volume 7. Thermal radiative properties - metallic elements and elements", ADA951941 available online at <https://ntrl.ntis.gov/NTRL/dashboard/searchResults/titleDetail/ADA951941.xhtml>
15. HASTELLOY HYBRID-BC1 datasheet, available online at <https://www.haynesintl.com/docs/default-source/pdfs/new-alloy-brochures/corrosion-resistant-alloys/brochures/hybrid-bc1.pdf>
16. J.P. Shingledecker, D.B. Glanton, R.L. Martin, B.L. Sparks, and R.W. Swindeman, "Tensile and Creep-Rupture Evaluation of a New Heat of Haynes Alloy 25", Oak Ridge National Lab, ORNL/TM-2006/609 (2007) available online at <https://www.osti.gov/biblio/901496>
17. H. Wang, W.D. Porter, H. Bottner, J. Konig, L. Chen, S. Bai, T.M. Tritt, A. Mayolet, J. Senawirantne, C. Smith, F. Harris, P. Gilbert, F.W. Sharp, J. Lo, H. Kleinke, and L. Kiss, Journal of Electronic Materials, v42, No. 4, p654 (2013) <https://doi.org/10.1007/s11664-012-2396-8>
18. B. Hay, O. Beaumont, N. Fleurence, et. al. , "Inter-laboratory Comparison on Thermal Diffusivity Measurements by the Laser Flash Method at Ultra-high Temperature", International Journal of Thermophysics , v44, No. 4, 48 (2023). <https://doi.org/10.1007/s10765-023-03159-5>
19. J. Chao, C.T. Lin, and T.H. Chung, "Vapor Pressure of Coal Chemicals", Journal of Physical and Chemical Reference Data, v12, No. 4, p1033 (1983) <https://srd.nist.gov/jpcrdreprint/1.555695.pdf>
20. National Oceanic and Atmospheric Administration (NOAA), CAMEO Chemical database <https://cameochemicals.noaa.gov/chemical/2577>
21. National Oceanic and Atmospheric Administration (NOAA), CAMEO Chemical database <https://cameochemicals.noaa.gov/chemical/4654>
22. A.S. Darling, "The Vapour Pressures of the Platinum Metals", Platinum Metals Review, v8, No. 4, p134 (1964) <https://doi.org/10.1595/003214064X84134140>
23. R.F. Hampson Jr. and R.F. Walker, "Vapor Pressures of Platinum, Iridium, and Rhodium", Journal of Research of the National Bureau Standards A Physics and Chemistry, v65A, No. 4, p289 (1961) [https://nvlpubs.nist.gov/nistpubs/jres/65A/jresv65An4p289\\_A1b.pdf](https://nvlpubs.nist.gov/nistpubs/jres/65A/jresv65An4p289_A1b.pdf)
24. C.B. Alcock, V.P. Itkin, and M.K. Horrigan, "Vapour Pressure Equations for the Metallic Elements: 298-2500 K", Canadian Metallurgical Quarterly, v23, No. 3, p309 (1984) <https://doi.org/10.1179/cmqr.1984.23.3.309>